



### Features 特性

- Thermal Conductivity 导热系数 8.0 W/m·K
- Natural Tackiness 自黏性
- Low Compress Stress 低压缩应力
- Low Thermal Resistance 低热阻

### Applications 产品应用

- Consumer Electronics 消费电子
- Network Equipment 网通设备
- Voltage Regulation Modules 电压调节模块
- High Speed Storage Drive 高速存储驱动器

**Thermal GP0800** 导热硅胶垫片是一款高导热性能的材料，双面微粘装配使用时，能够发热器件在散热片或金属底座之间构建良好的导热通路，低压缩力下表现出较低的热阻和较好的电气绝缘特性。

**Thermal GP0800** thermal conductive silicone gap pad is a kind of material with high thermal conductivity. Owing to double-sided natural tackiness, the material can build up a good heat conduction path between the heat sink and the metal substrate during assembly. The product shows low thermal resistance and good electrical insulation properties under low compression force.

Property 特性	Typical Value 典型值	Unit 单位	Test Method 测试方法
<b>Composition</b> 主要成分	Silicone Filled with Thermal Powder 硅胶&导热粉体	—	—
<b>Color</b> 颜色	Blue/Gray 蓝色/灰色	—	Visual 目视
<b>Thermal Conductivity</b> 导热系数	8.0	W/m·K	ASTM D5470
<b>Thickness</b> 厚度	0.5 - 5.0	mm	ASTM D374
<b>Hardness</b> 硬度 (Shore 00)	60 - 80	—	ASTM D2240
<b>Oil Bleeding</b> 渗油率	0.6	%	125°C 48H 50%压缩
<b>Density</b> 密度	3.5	g/cm <sup>3</sup>	ASTM D792
<b>Temperature Range</b> 耐温范围	-40 - 150	°C	—
<b>Breakdown Voltage</b> 击穿强度	6.0	KV/mm	ASTM D149
<b>Volume Resistivity</b> 体积电阻率	10 <sup>13</sup>	Ω.cm	ASTM D257
<b>Flame Rating</b> 阻燃等级	V-0	—	UL 94
<b>RoHS Compliance</b> 合规性	YES	—	—
<b>Shelf Life</b> 保存期	12	month	25±5°C ≤50% RH

All technical information stated in this technical data have been confirmed that all the technical parameters are reliable after harsh testing and evaluation of the products. Before you use our products, please carefully evaluate and decide whether the product meets your requirement and you need to take all the risks and responsibilities to use.

此技术资料里所有陈述的技术信息，全部是基于本公司对自身产品在经过严格的测试评估后，证明各项技术参数指标是值得信赖的前提下编写的。在您使用我们公司产品之前，请充分评估该产品是否符合您的使用需求，您需要承担使用的全部风险和责任。